

HABA Aluminium plates overview

Product overview, formats

G-Alu25, McBasic, Alu28, Alu35,
Planalu N, Planalu G, G-Alu340,
Alu6082, Alu50, Alu7075

Mechanical engineering

Vehicle construction

Plant construction

Apparatus construction

Jig manufacturing

Toolmaking



Product overview

Aluminium plates

HABA product designation	G-Alu25 milled	G-Alu25 sawn	McBasic
Material no.	-	-	-
Designation	similar EN AW-5083 AlMg4.5Mn0.7	similar EN AW-5083 AlMg4.5Mn0.7	similar EN AW-5083 AlMg4.5Mn0.7
State	homogenised	homogenised	casting plate
Surface	finely milled	cut by band saw	finely milled
HABA standard tolerance			
Surface tolerance	Ra0.8 (N6)	Ra25 (N12)	Ra0.8 (N6)
Thickness tolerance (mm)	+/-0.05	+1/0	+/-0.1
Parallelism (mm)	≤0.05	0.3	-
Evenness (mm)	≤0.2	0.3	-
Length and width tolerance (mm)	+0.8/+0.3	+0.8/+0.3	+1/0
Customer-specific tolerance	within a tolerance field of 0.4 mm	within a tolerance field of 0.4 mm	-
Mechanical properties			
Machinability	very good	very good	very good
Dimensional stability	very good	very good	good
Tensile strength R_m (N / mm ²)	≥250	≥250	≥250
Elastic limit $R_{p0.2}$ (N / mm ²)	≥115	≥115	≥115
Breaking strain A_5	6-10 %	6-10 %	6-10 %
Brinell hardness (HBS)	≥70	≥70	≥70
Weldability (WIG, MIG)	good	good	good
Behaviour by anodisation			
Decorative anodising	moderate	moderate	moderate
Protective anodising	very good	very good	very good
Use in contact with food	yes	yes	yes
Resistance			
Weatherproofness	very good	very good	very good
Seawater resistance	very good	very good	very good
Chemical composition			
Magnesium	Mg 4.0-4.9 %	4.0-4.9 %	4.0-4.9 %
Manganese	Mn 0.4-1.0 %	0.4-1.0 %	0.4-1.0 %
Chromium	Cr 0.05-0.25 %	0.05-0.25 %	0.05-0.25 %
Iron	Fe ≤0.40 %	≤0.40 %	≤0.40 %
Silicium	Si ≤0.40 %	≤0.40 %	≤0.40 %
Copper	Cu ≤0.10 %	≤0.10 %	≤0.10 %
Titanium	Ti ≤0.15 %	≤0.15 %	≤0.15 %
Zinc	Zn ≤0.25 %	≤0.25 %	≤0.25 %
Other elements together / individually	≤0.15 % / 0.05 %	≤0.15 % / 0.05 %	≤0.15 % / 0.05 %
Comments / comparisons			
	G-Alu25 is a naturally hardened aluminium casting plate which fulfils the most demanding machinability and dimensional stability requirements. The special casting process is the guarantee for the homogenous join and the vacuum tightness.	G-Alu25 is a naturally hardened aluminium casting plate which fulfils the most demanding machinability and dimensional stability requirements. The special casting process is the guarantee for the homogenous join and the vacuum tightness.	McBasic is a naturally hardened casting plate with good machinability and dimensional stability. Ideally suited for price-sensitive products in larger quantities.

Alu28	Alu35	Planalu G	Planalu N
3.3547 EN AW-5083 EN AW-AIMg4.5Mn0.7	3.3547 EN AW-5083 EN AW-AIMg4.5Mn0.7	3.3547 EN AW-5083 EN AW-AIMg4.5Mn0.7	3.3547 EN AW-5083 EN AW-AIMg4.5Mn0.7
H111	H111 / low-tension annealed	H111 / low-tension annealed	H111
finely milled	grinded	as-rolled	as-rolled
Ra0.8 (N6) +/-0.1 ≤0.1 ≤0.2 +0.8/+0.3 within a tolerance field of 0.4 mm	Ra1.6 (N7) +0.2/0 ≤0.1 ≤0.2 +0.8/+0.3 within a tolerance field of 0.4 mm	as-rolled EN 485-3/4 ≤0.2/100 ~0.5 +0.8/+0.3 within a tolerance field of 0.4 mm	as-rolled EN 485-3/4 ≤0.2/100 ~0.5 +0.8/+0.3 within a tolerance field of 0.4 mm
good good	good very good	good very good	good good
255-350 ≥105 ≥12 % ≥70	255-350 ≥105 ≥12 % ≥70	255-350 ≥105 ≥12 % ≥70	255-350 ≥105 ≥12 % ≥70
good	good	good	good
moderate very good	moderate very good	moderate very good	moderate very good
yes	yes	yes	yes
very good very good	very good very good	very good very good	very good very good
4.0-4.9 % 0.4-1.0 % 0.05-0.25 % ≤0.40 % ≤0.40 % ≤0.10 % ≤0.15 % ≤0.25 % ≤0.15 % / 0.05 %	4.0-4.9 % 0.4-1.0 % 0.05-0.25 % ≤0.40 % ≤0.40 % ≤0.10 % ≤0.15 % ≤0.25 % ≤0.15 % / 0.05 %	4.0-4.9 % 0.4-1.0 % 0.05-0.25 % ≤0.40 % ≤0.40 % ≤0.10 % ≤0.15 % ≤0.25 % ≤0.15 % / 0.05 %	4.0-4.9 % 0.4-1.0 % 0.05-0.25 % ≤0.40 % ≤0.40 % ≤0.10 % ≤0.15 % ≤0.25 % ≤0.15 % / 0.05 %
Alu28 is an annealed, naturally hard rolled plate with a precisely milled surface. The plates have an excellent parallelism, are easy to machine and dimensionally stable.	Alu35 is a low-tension annealed rolled plate with a grinded surface. The plates have excellent parallelism, are easy to machine and extremely dimensionally stable.	Planalu is a naturally hard rolled plate with good machinability and good dimensional stability. It is easy to weld, is extremely corrosion-resistant and suitable for metallic coatings. Planalu G is additionally low-tension annealed.	Planalu is a naturally hard rolled plate with good machinability and good dimensional stability. It is easy to weld, is extremely corrosion-resistant and suitable for metallic coatings.

Product overview

Aluminium plates

HABA product designation	Alu6082 milled	Alu6082 as-rolled	G-Alu340 milled
Material no.	3.2315	3.2315	-
Designation	EN AW-6082 EN AW-AISi1MgMn	EN AW-6082 EN AW-AISi1MgMn	- AlZn5Mg1
State	T6/T651	T6/T651	casting plate
Surface	finely milled	as-rolled	finely milled
HABA standard tolerance			
Surface tolerance	Ra0.8 (N6)	as-rolled	Ra0.8 (N6)
Thickness tolerance (mm)	+/-0.1	EN 485-3/4	+/-0.1
Parallelism (mm)	≤0.05	≤0.2/100	≤0.05
Evenness (mm)	≤0.2	≤0.5	≤0.2
Length and width tolerance (mm)	+0.8/+0.3	+0.8/+0.3	+0.8/+0.3
Customer-specific tolerance	within a tolerance field of 0.4 mm	within a tolerance field of 0.4 mm	within a tolerance field of 0.4 mm
Mechanical properties			
Machinability	good	good	very good
Dimensional stability	medium-good	medium-good	very good
Thickness in mm			
Tensile strength R_m (N / mm ²)	275-350	275-350	≥340
Elastic limit $R_{p0.2}$ (N / mm ²)	240-310	240-310	≥300
Breaking strain A_5	6-10 %	6-10 %	≥5 %
Brinell hardness (HBS)	84-104	84-104	≥110
Weldability (WIG, MIG)	very good	very good	very good
Behaviour by anodisation			
Decorative anodising	good	good	good
Protective anodising	very good	very good	good
Use in contact with food	yes	yes	no
Resistance			
Weatherproofness	very good	very good	good
Seawater resistance	very good	very good	good
Chemical composition			
Magnesium	Mg 0.7-1.3 %	0.7-1.3 %	≤0.1 %
Manganese	Mn 0.6-1.2 %	0.6-1.2 %	0.7-1.2 %
Chromium	Cr 0.4-1.0 %	0.4-1.0 %	0.045-0.125 %
Iron	Fe ≤0.25 %	≤0.25 %	0.08-0.24 %
Silicium	Si ≤0.5 %	≤0.5 %	0.095-0.2 %
Copper	Cu ≤0.1 %	≤0.1 %	≤0.05 %
Titanium	Ti ≤0.1 %	≤0.1 %	0.01-0.15 %
Zinc	Zn ≤0.2 %	≤0.2 %	5.0-6.0 %
Other elements together / individually	≤0.15 % / 0.15 %	≤0.15 % / 0.15 %	
Comments / comparisons			
	Alu6082 is an artificially aged rolled plate with a precisely milled or rolled surface. The material is very easy to machine and has medium to good dimensional stability. It has outstanding corrosion resistance against weather and seawater.	Alu6082 is an artificially aged rolled plate with a precisely milled or rolled surface. The material is very easy to machine and has medium to good dimensional stability. It has outstanding corrosion resistance against weather and seawater.	G-Alu340 is an aluminium casting plate with significantly higher dimensional stability than naturally hardened casting plates. We achieve the persistent equal strength with a multi-stage process of heat-treating and natural aging. The material stands out for its excellent machinability and great stability.

G-Alu340 sawn	Alu50	Alu7075 milled	Alu7075 as-rolled
-	3.4345	3.4365	3.4365
-	EN AW-7022	EN AW-7075	EN AW-7075
AlZn5.5Mg1	EN AW-AlZn5Mg3Cu	EN AW-AlZnMgCu1.5	EN AW-AlZnMgCu1.5
casting plate	T6/T651	T6/T651	T6/T651
cut by band saw	milled	milled	as-rolled
Ra25 (N11)	Ra0.8 (N6)	Ra0.8 (N6)	as-rolled
+1/0	+0.2/0	+/-0.1	EN 485-3/4
≤0.3	≤0.1	≤0.1	≤0.2/100
≤0.5	≤0.2	≤0.2	≤0.5
+0.8/+0.3	+0.8/+0.3	+0.8/+0.3	+0.8/+0.3
within a tolerance field of 0.4 mm	within a tolerance field of 0.4 mm	within a tolerance field of 0.4 mm	within a tolerance field of 0.4 mm
very good	very good	very good	very good
very good	good	medium-good	moderate
	<50 50-100 >100	<50 50-100 >100	<50 50-100 >100
≥340	≥450 ≥430 ≥410	≥500 ≥480-500 ≥400	≥500 ≥480-500 ≥400
≥300	≥370 ≥350 ≥330	≥450 ≥390-430 ≥280	≥450 ≥390-430 ≥280
≥5 %	≥7 % ≥5 % ≥3 %	3-8 % ≥2 % ≥2 %	3-8 % ≥2 % ≥2 %
≥110	≥125 ≥110 ≥100	≥140 ≥130 ≥120	≥140 ≥130 ≥120
very good	moderate	moderate	moderate
good	moderate	bad or unsuitable	bad or unsuitable
good	good	good	good
no	no	no	no
good	moderate	moderate	moderate
good	moderate	moderate	moderate
≤0.1 %	≤0.5 %	≤0.4 %	≤0.4 %
0.7-1.2 %	2.6-3.7 %	2.1-2.9 %	2.1-2.9 %
0.045-0.125 %	0.1-0.4 %	≤0.3 %	≤0.3 %
0.08-0.24 %	0.1-0.3 %	0.18-0.28 %	0.18-0.28 %
0.095-0.2 %	≤0.5 %	≤0.5 %	≤0.5 %
≤0.05 %	0.5-1.0 %	1.2-2.0 %	1.2-2.0 %
0.01-0.15 %	≤0.2 % (Ti+Zr)	≤0.2 % (Ti+Zr ≤0.25 %)	≤0.2 % (Ti+Zr ≤0.25 %)
5.0-6.0 %	4.3-5.2 %	5.1-6.1 %	5.1-6.1 %
		≤0.15 % / ≤0.15 %	≤0.15 % / ≤0.15 %
G-Alu340 is an aluminium casting plate with significantly higher dimensional stability than naturally hardened casting plates. We achieve the persistent equal strength with a multi-stage process of heat-treating and natural aging. The material stands out for its excellent machinability and great stability.	Alu50 is an artificially aged and additionally low-tension annealed rolled plate with high tensility and good machinability. The material also has a great hardness and a very good dimensional stability.	Alu7075 is an artificially aged rolled plate with very high tensility and hardness. The material can be easily machined. Slight bending is possible.	Alu7075 is an artificially aged rolled plate with very high tensility and hardness. The material can be easily machined. Slight bending is possible.

HABA storage formats

	G-Alu25	G-Alu25	McBasic	Alu28	Alu35	Planalu G	Planalu N
Standard format in mm Max format in mm	1600 x 3000 2350 x 4250	1600 x 3000 2350 x 4250	2070 x 4000	1520 x 3020 2010 x 3020	1003 x 3020 2010 x 3020	1520 x 3020	1520 x 3020
Thickness in mm	finely milled	cut by band saw	finely milled	finely milled	grinded	as-rolled	as-rolled
3	◆						
4	◆						
5	◆			◆	◆	◆	◆
6	◆			◆	◆	◆	◆
7	◆						
8	◆		◇	◆	◆	◆	◆
9	◆						
10	◆		◇	◆	◆	◆	◆
11	◆						
12	◆		◇	◆	◆	◆	◆
13	◆						
14	◆		◇	◆	◆	◆	◆
15	◆						
16	◆						
17	◆						
18	◆						
19	◆		◇	◆	◆	◆	◆
20	◆						
21	◆	21 +1/0 ◆					
22	◆						
23	◆						
24	◆		◇	◆	◆	◆	◆
25	◆						
26	◆	26 +1/0 ◆					
27	◆						
28	◆						
29	◆		◇	◆	◆	◆	◆
30	◆	31 +1/0 ◆					
35	◆		◇	◆	◆	◆	◆
40	◆	36 +1/0 ◆	◇	◆	◆	◆	◆
45	◆	41 +1/0 ◆	◇	◆	◆	◆	◆
50	◆		◇	◆	◆	◆	◆
60	◆	51 +1/0 ◆	◇	◆	◆	◆	◆
70	◆	61 +1/0 ◆ 71 +1/0 ◆	◇		◆	◆	◆
80	◆		◇		◆	◆	◆
90	◆	81 +1/0 ◆	◇		◆	◆	◆
100	◆	91 +1/0 ◆ 101 +1/0 ◆	◇		◆	◆	◆
110	◆	111 +1/0 ◆				◆	◆
120	◆	121 +1/0 ◆				◆	◆
130	◆					◆	◆
140	◆					◆	◆
150	◆					◆	◆
160	◆					◆	◆

◆ 1-3 days delivery
◇ 5 days delivery

On request we can also produce special thicknesses and special tolerances
Subject to changes in stocks

	Alu6082	Alu6082	G-Alu340	G-Alu340	Alu50	Alu7075	Alu7075
Standard format in mm	1520 x 3020	1520 x 3020	1550 x 3000	1550 x 3000	1500 x 3000	1520 x 3020	1520 x 3020
Thickness in mm	finely milled	as-rolled	finely milled	cut by band saw	finely milled	finely milled	as-rolled
3							
4							
5		◆					
6		◆	◆		◆		
7							
8	◆	◆	◆		◆		
9							
10	◆	◆	◆		◆	◆	◆
11							
12	◆	◆	◆		◆	◆	◆
13							
14							
15	◆	◆	◆		◆	◆	◆
16							
17							
18							
19							
20	◆	◆	◆		◆	◆	◆
21							
22				21 +1/0	◆		
23							
24							
25	◆	◆	◆		◆	◆	◆
26							
27				26 +1/0	◆		
28							
29							
30	◆	◆	◆	31 +1/0	◆	◆	◆
35							
40	◆	◆	◆	36 +1/0	◆	◆	◆
45				41 +1/0	◆	◆	◆
50							
60				51 +1/0	◆	◆	◆
70				61 +1/0	◆	◆	◆
				71 +1/0	◆		
80							
90				81 +1/0	◆	◆	◆
100				91 +1/0	◆	◆	◆
				101 +1/0	◆		
110		◆			◆		◆
120		◆			◆		◆
130		◆			◆		◆
140		◆			◆		◆
150		◆			◆		◆
160		◆			◆		◆

◆ 1-3 days delivery
◇ 5 days delivery

On request we can also produce special thicknesses and special tolerances
Subject to changes in stocks

Our brand promise

Maximum availability and tailor-made production possibilities with high-quality steel and aluminium plates give ambitious customers certainty and confidence.

Flexible solutions and consistently high quality makes HABA to the right partner for mechanical- and plant-engineering.

HABA brand equity / value

Flexible and fast solutions
100% reliability, no surprises
Experienced and qualified consultation
Maximum availability
Persistence and constancy

HABA quality guarantee

HABA material from the best pre-material quality
HABA products on request with specially tested material
HABA material with 3.1 certificate available
HABA quality management according to ISO 9001
HABA products on request with complete traceability
HABA tailor-made solutions in dimension and tolerance



HABA AG
Gewerbstrasse 6
CH-6330 Cham/ZG

Tel. +41 (0)41 748 88 88
Fax +41 (0)41 748 88 11
info@haba.ch
www.haba.ch

HABA PlattenService GmbH
Einsteinstrasse 7
D-71083 Herrenberg

Tel. +49 (0)7032 97 570
Fax +49 (0)7032 76 863
info@haba-gmbh.de
www.haba-gmbh.de

HABA ServizioPiastre S.r.l.
Via Emilia, 27/29
I-24052 Azzano San Paolo (BG)

Tel. +39 (0)35 899 190
Fax +39 (0)35 899 167
info@haba.it
www.haba.it

HABA GmbH
Anrissenweg 6
A-2345 Brunn am Gebirge

Tel. +43 (0)722 867 488
Fax +43 (0)722 867 477
info@haba-gmbh.at
www.haba-gmbh.at

HABA Czech s.r.o.
Litobratřická 686
Hrušovany nad Jevišovkou
CZ-671 67

Tel. +420 515 225 121
Fax +420 515 224 757
info@haba-sro.cz
www.haba-sro.cz