

# HABA Alu50

Milled, high-tensile aluminium rolled plates  
cut to size

Alu50 is an artificially aged and additionally low-tension annealed rolled sheet with high tensility and good machinability. The material also has a great hardness and a very good dimensional stability.

## FINISHES

Thickness	precisely milled Ra0.8 (N6)
Tolerance	+0.2/0 mm
Protective film	one-sided
Cardboard	one-sided
Parallelism	≤0.1 mm
Evenness	≤0.2 mm
Length/width	Ra3.2-6.3 cut with a precision circular saw
HABA standard tolerance	nominal size +0.8/+0.3 mm
Customer-specific tolerance	within a tolerance field of 0.4 mm

We also produce other thicknesses and tolerances on request.

## TECHNICAL SPECIFICATIONS

Thickness (mm)	<50	50-100	>100
Tensile strength $R_m$ (N/mm <sup>2</sup> )	≥450	≥430	≥410
typical values	~520	~490	~470
Yield strength $R_{p0.2}$ (N/mm <sup>2</sup> )	≥370	≥350	≥330
typical values	~460	~430	~400
Breaking strain ( $L_o = 5 d_o$ )			
$A_5$	≥7%	≥5%	≥3%
typical values	~9%	~8%	~5%
Brinell hardness (HBS)	≥125	≥110	≥100
Density	2.78 kg/dm <sup>3</sup>		
E-module	~71.000 N/mm <sup>2</sup>		
Thermal conductivity coefficient	130-160 W/mK		
Thermal expansion coefficient	23.6 x 10 <sup>-6</sup> /K		
Electrical conductivity	19-23 m/Ω mm <sup>2</sup>		
State	T6	<10 mm	
	T651	>10 mm	

## CHEMICAL COMPOSITION

Magnesium	Mg	2.60-3.70 %	Silicium	Si	≤0.50 %
Manganese	Mn	0.10-0.40 %	Copper	Cu	0.50-1.00 %
Chromium	Cr	0.10-0.30 %	Zinc	Zn	4.30-5.20 %
Iron	Fe	≤0.50 %	Ti + Zr		≤0.20 %

DIN Material no.	3.4345
Designation	EN AW-7022 EN AW-AlZn5Mg3Cu
Material code	AlZnMgCu0.5
State	T6/T651

## MATERIAL IN USE

Special purpose machinery  
Jig manufacturing  
Prototype construction  
Mechanical engineering  
Toolmaking  
Mould construction  
Plant construction

## APPLICATIONS

Base plates  
Rotary tables  
Pattern plates

## PROPERTIES

machinability	very good
dimensional stability	good
tensility	high
hardness	high
Contact with foodstuffs	no

## SURFACE TREATMENT

Decorative anodisation:	moderate
Protective anodisation:	good
Paintwork, coating:	good
Galvanic coating:	good
Chemical nickel coating:	excellent

## INSTRUCTIONS

HABA Alu50 is well suited for machining. Use tools for working aluminium with a cutting speed >2000 m/min. Decreasing rigidity in the core of thick plates.

We declare that our products are not suitable for any other applications and purposes, other than those specified here and do not have other product properties than those specified here.

